

喜利得股份有限公司
 喜利得台灣工程與服務實驗室
Hilti Taiwan Engineering and Services Testing Lab.
 NO.57, Gangshan Rd., Gangshan Dist., Kaohsiung City, Taiwan
 TEL : 886 - 7 - 6295982 FAX : 886 - 7 - 6295983

TEST REPORT

TEST REPORT NO.: TS20005		TEST METHOD:		
ITEM DESCRIPTION: Motek treskrue røroppheng M8/M10		CE 14566		
SAMPLE RECEIVE DATE : 2020/02/19				
REPORT DATE : 2020/02/21	TEST DATE: 2020/02/19	NOTES FOR SAMPLE:		
CLIENT : Motek treskrue røroppheng		10 pcs		
CLIENT ADDRESS:				
	TEST ITEM	SPECIFICATION(Unit)	TEST RESULT	NOTE
1	Withdraw force	Min. 1000 Newton	7130.04 ~ 8371.21	
2	Blank below			
3				

Wood specification

Wood	Density	Wood level
Southern Pine	0.38 g/cm ³	C24



Page 1 of 1

QP2401-1.0

Remark:

1. This test report only relates to the item(s) listed and tested. Partial use of this report is not valid.
2. Samples tested per the requirements of specification
3. This test report is responsible for designated samples only.
4. Inspection characteristics marked with "☆" are not accredited by TAF.
5. Inspection characteristics marked with "◎" are certified by an accredited third party lab as indicated.

Lab. Manager(Signature)