

Evidence of Performance

Joint sound reduction of filling material

Test report

No. 17-001757-PR02

(PB Z1-K02-04-en-01)



Client **Hilti Entwicklungsgesellschaft mbH**
Hiltistr. 6
86916 Kaufering
Germany

Basis

EN ISO 10140-1: 2016
EN ISO 10140-2 : 2010
EN ISO 717-1 : 2013

Test report 17-001757-PR02
(PB Z1-K02-04-de-01) dated
29.06.2017

Representation



Product	intumescent acrylate-fire stop compound
Designation	Hilti Firestop Intumescent Sealant CFS-IS / CP 611A
Density	1.57 kg/rm
Special features	-/-

Instructions for use

This procedure is suitable for the comparison of construction products designed for sealing (e.g. gaskets/seals, fillers for joints). The results can be used to evaluate the sound power ratio τ_0 according to EN 12354-3 Annex B.

Using the calculated sound reduction of the joint for the calculation of the overall sound reduction is not a substitute for the sound reduction verification of the overall construction.

Weighted sound reduction index of joints $R_{s,w}$
Spectrum adaptation terms C and C_{tr}



$$[R_{s,w} (C; C_{tr}) \geq 64 (-2; -5) \text{ dB}]$$

Determined for 25 mm width of joint

ift Rosenheim
19.07.2017

Dr. Joachim Hessinger, Dipl.-Phys.
Head of Testing Department
Building Acoustics

Bernd Saß, Dipl.-Ing. (FH)
Operating Testing Officer
Building Acoustics

Validity

The data and results given relate solely to the tested and described specimen.

Testing the sound insulation does not allow any statement to be made on any further characteristics of the construction submitted regarding performance and quality.

Notes on publication

The ift Guidance Sheet "Conditions and Guidance for the Use of ift Test Documents" applies.

The cover sheet can be used as an abstract.

Contents

The test report contains a total of 10 pages:

- 1 Object
 - 2 Procedure
 - 3 Detailed results
 - 4 Instructions for use
- Data sheet (1 page)

Joint sound reduction of filling material

Test report 17-001757-PR02 (PB Z1-K02-04-en-01) dated 19.07.2017

Client Hilti Entwicklungsgesellschaft mbH, 86916 Kaufering (Germany)

**1 Object****1.1 Description of test specimen**

Product	intumescent acrylate-fire stop compound, joint sealed on both sides
Date of manufacturing of test specimen	7th of June 2017
Product designation	Hilti Firestop Intumescent Sealant CFS-IS / CP 611A
Item code	2004614
Dimension	
Joint of length l	1,200 mm
Depth of joint d	100 mm
Width of joint w	25 mm
Joint cover	Without cover
Joint sealing material	Joint filled with mineral wool and sealed on both sides with acrylate - sealant
Curing time	19 days
Density	1.57 kg/rm (determined at test element incl. mineral wool)
Sealant thickness (nominal dimensions)	25 mm

The description is based on inspection of the test specimen at the **ift** Laboratory for Building Acoustics. Item designations / numbers as well as material specifications were provided by the client. (Additional data provided by the manufacturer are marked with *).

1.2 Mounting to test rig

The sound reduction index R_s of the joint was measured in a mobile joint measuring apparatus as per EN ISO 10140-1:2016 (see Figs. 1 and 2). This mobile measuring apparatus consists of a high-performance sound insulating element made of metal profiles and Bondal sheet with slide-in cassettes; the profiles of the slide-in cassettes are filled with sand. Using these cassettes, a great variety of joints with varying joint widths w can be created (Fig. 1).




Fig 1 slide-in cassettes

These slide-in cassettes were filled 19 days before the test by **ift** Laboratory for Building Acoustics and employees of the client with the filling material acc. to the guideline of the manufacturer. After hardening the material was cut on the edges and mounted in the highly sound insulating element (Fig. 2), which was mounted in the test opening of the win-

Joint sound reduction of filling material

Test report 17-001757-PR02 (PB Z1-K02-04-en-01) dated 19.07.2017

Client **Hilti Entwicklungsgesellschaft mbH**, 86916 Kaufering (Germany)

dow-test rig (Z-wall) acc. to EN ISO 10 140-5. The joints to the test opening were filled with cellular material and sealed with plastic sealant on both sides.




fig 2 Set-up of joint testing apparatus (high performance sound insulating element)



fig 3 Photo(s) of the mounted element, taken by ift Laboratory for Building Acoustics

Joint sound reduction of filling material

Test report 17-001757-PR02 (PB Z1-K02-04-en-01) dated 19.07.2017

Client **Hilti Entwicklungsgesellschaft mbH**, 86916 Kaufering (Germany)**2 Procedure****2.1 Sampling**

Sampling	The samples were selected by the client. The slide-in cassettes were filled by the ift Laboratory for Building Acoustics with the filler to be tested according to the instructions of the manufacturer.
Quantity	1
Manufacturer	Hilti AG, BU Fire Protection, Feldkircherstr. 100, FL-9494 Schaan
Manufacturing plant	Hilti Plant 4a
Date of manufacture /	1.7.2016
Date of sampling	
Batch	4003487
Responsible for sampling	Mr. Schulze
Delivery at ift	7.6.2017 by the client
ift registration number	43840/1

2.2 Process**Basis**

EN ISO 10140-1:2016	Acoustics; Laboratory measurement of sound insulation of building elements - Part 1: Application rules for specific products (ISO 10140-1: 2016); German version EN ISO 10140-1:2016
EN ISO 10140-2:2010	Acoustics; Laboratory measurement of sound insulation of building elements - Part 2: Measurement of airborne sound insulation (ISO 10140-2:2010)
EN ISO 717-1: 2013	Acoustics; Rating of sound insulation in buildings and of building elements - Part 1: Airborne sound insulation

Corresponds to the national German standard/s:

DIN EN ISO 10140-1:2016-12, DIN EN ISO 10140-2:2010-12 and DIN EN ISO 717-1 : 2013-06

Additional basis

ASTM E 90-09	Standard test method for laboratory measurement of airborne sound transmission loss of building partitions and elements
ASTM E 413-10	Classification for rating sound insulation

Boundary conditions

As specified by the standard.

Deviation

There are no deviations from the test method/s and/or test conditions acc. to EN ISO 10140.

The volume of the test room falls below the minimum volume of 80 m³ as defined in ASTM 90:2009.

Joint sound reduction of filling material

Test report 17-001757-PR02 (PB Z1-K02-04-en-01) dated 19.07.2017

Client Hilti Entwicklungsgesellschaft mbH, 86916 Kaufering (Germany)



Test noise	Pink noise
Measuring filter	One-third-octave band filter
Measurement limits	
Low frequencies	The dimensions of the receiving room are smaller than recommended for testing in the frequency range from 50 Hz to 80 Hz as per EN ISO 10140-4:2010 Annex A (informative). A moving loudspeaker was used.
Background noise level	The background noise level in the receiving room was determined during measurement and the receiving room level L_2 corrected by calculation as per EN ISO 10140-4: 2010 Clause 4.3.
Maximum insulation	The maximum insulation of the test rig is partly within the range of the test results. Therefore the tested values are minimum values. A correction by calculation was performed for maximum sound insulation.
Measurement of reverberation time	Arithmetical mean: two measurements each of 2 loudspeaker and 3 microphone positions (a total of 12 independent measurements).
Measurement equation A	$A = 0,16 \cdot \frac{V}{T} \text{ m}^2$
Measurement of sound level difference	Minimum of 2 loudspeaker positions and rotating microphones.
Measurement equation	$R_s = L_1 - L_2 + 10 \log \frac{S_N \cdot l}{A \cdot l_N} \text{ dB}$

KEY

R_{ST}	Joint sound reduction index in dB
L_1	Sound pressure level source room in dB
L_2	Sound pressure level receiving room in dB
l	Length of joint in m
S_N	Reference area (1 m ²)
l_N	Reference length (1 m)
A	Equivalent absorption area in m ²
V	Volume of receiving room in m ³
T	Reverberation time in s

Joint sound reduction of filling material

Test report 17-001757-PR02 (PB Z1-K02-04-en-01) dated 19.07.2017

Client Hilti Entwicklungsgesellschaft mbH, 86916 Kaufering (Germany)

**2.3 Test apparatus**

Device	Type	Manufacturer
Integrating sound meter	Type Nortronic 121	Norsonic-Tippkemper
Microphone preamplifiers	Type 1201	Norsonic-Tippkemper
Microphone unit	Type 1220	Norsonic-Tippkemper
Calibrator	Type 1251	Norsonic-Tippkemper
Dodecahedron loudspeakers	Own design	-
Amplifier	Type E120	FG Elektronik
Rotating microphone boom	Own design / Type 231-N-360	Norsonic-Tippkemper

The **ift** Laboratory for Building Acoustics participates in comparative measurements at the Physikalisch-Technische Bundesanstalt (PTB) in Braunschweig every three years, the last one was in April 2016. The sound level meter used, Series No. 31423, was DKD calibrated by the company Norsonic Tippkemper (DKD - Deutscher Kalibrierdienst "German Calibration_Service") on 22nd of May 2017.

2.4 TestingDate 26th of June 2017

Operating Testing Officer Mr. Bernd Saß

3 Detailed results

The values of the measured sound reduction index R_S of the joint for the tested filler are plotted against frequency in the data sheets (Annex). Based on EN ISO 717 - 1, this is used to calculate the weighted sound reduction index $R_{S,w}$ of the joint and the spectrum adaptation terms C and C_{tr} , related to joint length $l = 1.20$ m, for the frequency range 100 Hz to 3,150 Hz.

The diagram includes the maximum sound reduction of the test set-up (related to $l = 1.20$ m), plotted with a maximum weighted sound reduction index $R_{S,w \max}(C; C_{tr}) = 63 (-2; -5)$ dB

The resulting sound reduction indices for joints are within the range for maximum sound insulation; in these cases the values obtained are minimum values. For maximum insulation, it has been corrected by calculation as per EN ISO 10140-1:2016, annex J. Table 1 lists the weighted sound reduction indices of the different joint designs.

Joint sound reduction of filling material

Test report 17-001757-PR02 (PB Z1-K02-04-en-01) dated 19.07.2017

Client Hilti Entwicklungsgesellschaft mbH, 86916 Kaufering (Germany)

**Table 1** Test results, joint depth $d = 100$ mm

Weighted joint sound reduction index $R_{S,w}(C; C_{tr})$ in dB	Measures taken, comments
63 (-2;-5)	Maximum sound insulation
≥ 64 (-2;-5)	Joint width 25 mm, filled with Hilti Firestop Intumescent Sealant CFS-IS / CP 611A

On order of the client supplementary to the rating as per EN ISO 717-1 a weighting according to ASTM E 413-10 was carried out. The sound transmission class STC according to ASTM E 413-10 was determined for the frequency range from 125 Hz up to 4,000 Hz

STC 64

The rating was done with spectrum of joint sound reduction index which is tabled in annexed data sheet.

4 Instructions for use**4.1 Application for DIN 4109: 2016-07****Basis**

DIN 4109-1: 2016-07	Sound insulation in buildings - Part 1: Minimum requirements
DIN 4109-2: 2016-07	Sound insulation in buildings - Part 2: Verification of compliance with the requirements by calculation

The weighted joint sound reduction index determined in accordance with Section 3, can be directly used for verification of sound insulation by calculation in accordance with DIN 4109-2.

This sound reduction index of joints is comparable to the linear sound reduction index of a building component with 1 m joint length for each m^2 area and where the sound is transmitted only through the joint.

If the joint is combined with a building component (e.g. window with area S and weighted sound reduction index R) and assuming the building component's area $S_1 \gg$ than the opening area of the joint ($w \cdot l$, w = joint width), for the associated joint length l and a reference length $l_0 = 1$ m the resulting sound reduction index $R_{i,w}$ of the i -th-window with installation joint is calculated as follows:

$$R_{i,w} = -10 \cdot \log \left(10^{\frac{R_w}{10}} + \frac{l \cdot l_0}{S} \cdot 10^{\frac{R_{s,w}}{10}} \right) \text{ dB}$$

Joint sound reduction of filling material

Test report 17-001757-PR02 (PB Z1-K02-04-en-01) dated 19.07.2017

Client Hilti Entwicklungsgesellschaft mbH, 86916 Kaufering (Germany)



For calculation of the total weighted apparent sound reduction index $R'_{w,ges}$ in accordance with DIN 4109-2 Clause 4, the input data obtained from laboratory measurements must be stated in $1/10$ dB. For the involvement of sound transmission via installation joint the resulting weighted joint sound reduction index can then be applied directly to the joint sound insulation. This gives:

$$R_{S,w} = 64.6 \text{ dB (width of joint 25 mm)}$$

4.2 Uncertainty of measurement, single number ratings in $1/10$ dB

Basis

EN ISO 12999-1: 2014 Acoustics; Determination and application of measurement uncertainties in building acoustics, part 1: sound insulation (ISO 12999-1: 2014)

The resulting weighted sound reduction index of joints (in $1/10$ dB with measurement uncertainty), determined on the basis of EN ISO 717-1:2013-06 is:

$$R_{S,w} = 64.6 \text{ dB} \pm 1.2 \text{ dB (width of joint 25 mm)}$$

The specified measurement uncertainty is the average standard deviation of laboratory measurements (standard measurement uncertainty σ_R for measurement situation A: Characterisation of a building component by laboratory measurements as per EN ISO 12999-1:2014, Table 3 $\sigma_R = 1.2$ dB).

The product declaration must use the integral value of the joint sound reduction index and the spectrum adaptation terms as given in Section 3.

$$R_{S,w} (C;C_{tr}) \geq 64 \text{ (-2;-5) dB (width of joint 25 mm)}$$

4.3 General remarks:

The method is suitable for comparing construction products designed for sealing purposes (e.g. seals/gaskets, fillers to seal joints). The results can be used to evaluate the sound power ratio τ_e as per EN 12354-3 Annex B. Using the calculated sound reduction of the joint for the calculation of the overall sound reduction is not a substitute for the verification of the overall construction

In practice, e.g. when combining the sound insulation of a window with that of a joint in an existing opening, the following must be taken into account:

- For physical reasons, the sound reduction index of joints must be corrected by approx. -3 dB in the area of corners and edges;
- The existing thickness of the window frame profile (joint depth d) must be adapted with a correction between -1 dB and -2 dB.

Joint sound reduction of filling material

Test report 17-001757-PR02 (PB Z1-K02-04-en-01) dated 19.07.2017

Client **Hilti Entwicklungsgesellschaft mbH**, 86916 Kaufering (Germany)



- c) Experience shows that the filling of window niches in edges and difficult reachable areas are weak points by handling

Remark on transfer of the test results

Assessments as per ASTM E 413-10 were based on sound insulation testing as per EN ISO 10140-1. For some details there are deviations from test standard ASTM E 90-09, in particular as regards the required room volume (min. 80 m³) and regards the sound reduction index of joints (length related sound reduction index).

ift Rosenheim

Laboratory for Building Acoustics

19.07.2017

Joint sound reduction index according to ISO 10140-1

Determination of sound reduction index of joints

Client: **Hilti Entwicklungsgesellschaft mbH**,
86916 Kaufering, Germany

Product designation Hilti Firestop Intumescent Sealant CFS-IS / CP 611A



Design of test specimen

intumescent acrylate-fire stop compound

Joint size

Length l 1,200 mm

Depth d 100 mm

Width w 25 mm

Density 1.57 kg/rm

Test date 26th of June 2017

Test length l 1.2 m

Test rig as per EN ISO 10140-5

Test rig separation wall Double-leaf concrete wall, insert frame

Test noise Pink noise

Volumes of test room $V_S = 104 \text{ m}^3$
 $V_R = 67.5 \text{ m}^3$

Maximum joint sound reduction index

$R_{S,w,max} = 63 \text{ dB}$ (related to test length)


Mounting conditions

Mounting of the cassette in high performance sound insulating element.

Climate in test rigs 24°C / 50 % RH


Static air pressure 959 hPa

Drawing of the test arrangement



f in Hz	R_S in dB
50	(≥ 37.0)
63	(≥ 36.8)
80	(≥ 45.6)
100	(≥ 50.1)
125	(≥ 47.3)
160	(≥ 49.8)
200	(≥ 49.3)
250	(≥ 52.1)
315	(≥ 55.8)
400	(≥ 58.8)
500	(≥ 61.5)
630	(≥ 63.6)
800	(≥ 66.9)
1,000	(≥ 66.7)
1,250	(≥ 67.1)
1,600	(≥ 68.1)
2,000	(≥ 69.0)
2,500	(≥ 70.1)
3,150	(≥ 68.4)
4,000	(≥ 69.4)
5,000	(≥ 69.0)

(\geq = minimum value)



Rating according to EN ISO 717-1 (in third octave bands):

$[R_{S,w} (C; C_{tr}) \geq 64 (-2; -5) \text{ dB}]$ $C_{50-3,150} = -2 \text{ dB}$; $C_{100-5,000} = -1 \text{ dB}$; $C_{50-5,000} = -1 \text{ dB}$
 $C_{tr,50-3,150} = -9 \text{ dB}$; $C_{tr,100-5,000} = -5 \text{ dB}$; $C_{tr,50-5,000} = -9 \text{ dB}$

Test report no.: 17-001757-PR02 (PB Z1-K02-04-en-01)

Page 10 of 10, **Data sheet 1**

ift Rosenheim

Laboratory for Building Acoustics

19. July 2017

Bernd S./S
Dipl. Ing. (FH) Mr. Bernd Saß
Operating Testing Officer